



National Aeronautics and
Space Administration

Washington, D.C.
20546

Headquarters

JUN 21 1982

Reply to Attn of: GP-4

TO: NST-44/Scientific and Technical Information Division
Attn: Shirley Peigare

FROM: GP-4/Office of Assistant General Counsel
for Patent Matters

SUBJECT: Announcement of NASA-Owned U.S. Patents in STAR

In accordance with the procedures agreed upon by Code GP-4 and Code NST-44, the attached NASA-owned U.S. Patent is being forwarded for abstracting and announcement in NASA STAR.

The following information is provided:


U.S. Patent No. : 3,811,901
United Aircraft Corporation
Government or
Contractor Employee: East Hartford, Conn.
NASA Case No. : HQN-10,328-2

NOTE - If this patent covers an invention made by a contractor employee under a NASA contract, the following is applicable:

YES ☒

NO ☐

Pursuant to Section 305(a) of the National Aeronautics and Space Act, the name of the Administrator of NASA appears on the first page of the patent; however, the name of the actual inventor (author) appears at the heading of Column No. 1 of the specification, following the words "...with respect to an invention of...."



(NASA-Case-HQN-10328-2) NON-TOXIC INVERT
ANALOG GLASS COMPOSITIONS OF HIGH MODULUS
Patent (National Aeronautics and Space
Administration) 5 p

N82-29454

CSCL 11C

Unclas

00/27 24154

United States Patent [19]

Bacon

HQN-101 328-2

[11] 3,811,901

[45] May 21, 1974

[54] NON-TOXIC INVERT ANALOG GLASS COMPOSITIONS OF HIGH MODULUS

[75] Inventor: James F. Bacon, Manchester, Conn.

[73] Assignee: United Aircraft Corporation, East
Hartford, Conn.

[22] Filed: Apr. 21, 1972

[21] Appl. No.: 246,294

Related U.S. Application Data

[63] Continuation-in-part of Ser. No. 874,673, Nov. 6,
1969, abandoned.

[52] U.S. Cl. 106/50, 106/52, 106/54

[51] Int. Cl. C03c 3/04

[58] Field of Search. 106/50, 52, 54

[56] References Cited

UNITED STATES PATENTS

2,805,166 9/1957 Löffler 106/52
3,573,078 3/1971 Bacon 106/52

3,060,041 10/1962 Lowenstein 106/50
3,183,104 5/1965 Thomas 106/50
3,484,259 12/1969 Lewis et al. 106/50
3,166,428 1/1965 Thomas 106/50

Primary Examiner—Helen M. McCarthy

Attorney, Agent, or Firm—John D. Del Ponti

[57] ABSTRACT

Glass compositions having a Young's modulus of at least 15 million psi and a specific modulus of at least 110 million inches consisting essentially of, in mols, 15–40% SiO₂, 6–15% Li₂O, 24–45 percent of at least two bivalent oxides selected from the group consisting of Ca, ZnO, MgO and CuO; 13–39 percent of at least two trivalent oxides selected from the group consisting of Al₂O₃, Fe₂O₃, B₂O₃, La₂O₃, and Y₂O₃ and up to 15 percent of one or more tetravalent oxides selected from the group consisting of ZrO₂, TiO₂ and CeO₂.

8 Claims, No Drawings

NON-TOXIC INVERT ANALOG GLASS COMPOSITIONS OF HIGH MODULUS

BACKGROUND OF THE INVENTION

This application is a continuation-in-part of application Ser. No. 874,673 filed Nov. 6, 1969 by the same inventor and now abandoned.

The invention described herein was made in performance of work under a NASA contract and is subject to the provisions of Section 305 of the National Aeronautics and Space Act of 1958, Public Law 85-568 (72 Stat. 435; 42 USC 2457).

This invention relates to high modulus glass and glass compositions and more particularly relates to invert glasses having a Young's modulus of at least 15 million psi, a specific modulus of at least 110 million inches and containing no toxic elements.

In the present age, there has been a continuing search for glasses of high modulus and low density, capable for use as reinforcements, preferably in fiber form, in composite structures ranging from high strength missile cases and helicopter blades to propeller spinners and gas turbine engine parts. Glass offers promise as the reinforcements in such applications since it may be quickly and cheaply produced by relatively conventional techniques and, generally, presents no compatibility problems with the matrix materials with which it is normally used. There is a need however, to provide glass formulations which possess a high modulus of elasticity, and preferably a high modulus-density ratio. It is even more preferable if the glass possess the aforementioned two characteristics in combination with an appropriate liquidus-viscosity relationship to permit fiberization. Furthermore, in most commercial applications, it is important that the glasses contain no toxic elements, such as beryllia or thoria, which may present complications either in their manufacture or in their use.

SUMMARY OF THE INVENTION

The glass compositions of the present invention are a high modulus, low density invert glass which, in their preferred form consist essentially of a combination of silica, the monovalent oxide of lithium, two or more bivalent oxides selected from the group consisting of CaO, ZnO, MgO and CuO, and at least two trivalent oxides selected from the group consisting of Al_2O_3 , Fe_2O_3 , B_2O_3 , La_2O_3 and Y_2O_3 . More particularly, the inventive glasses contemplated are those having a Young's modulus of at least 15 million psi and a specific modulus of at least 110 million inches which consists essentially of 15-40 mol % SiO_2 , 6-15 mol % Li_2O , 24-45 mol percent of at least two bivalent oxides selected from the group consisting of CaO, ZnO, MgO and CuO, 13-39 mol percent of at least two trivalent oxides selected from the group consisting of Al_2O_3 , Fe_2O_3 , B_2O_3 , La_2O_3 and Y_2O_3 and up to 15 mol percent of one or more tetravalent oxides selected from the group consisting of ZrO_2 , TiO_2 and CeO_2 . It will be noted that the glasses are comprised of only one alkali oxide and a combination of alkaline earth oxides and trivalent and tetravalent oxides.

Preferably, the inventive glasses are those having a Young's modulus of at least 15 million psi and a specific modulus of at least 110 million inches which consists essentially of 15-40 mol % SiO_2 , 6-15 mol % Li_2O ,

12-24 mol % MgO , 3-30 mol percent of at least one bivalent oxide selected from the group consisting of CaO, ZnO and CuO, the total amount of MgO and said bivalent oxides being 24-45 mol percent, 13-39 mol percent of at least two trivalent oxides selected from the group consisting of Al_2O_3 , Fe_2O_3 , B_2O_3 , La_2O_3 and Y_2O_3 , and up to 15 mol percent of one or more tetravalent oxides selected from the group consisting of ZrO_2 , TiO_2 , and CeO_2 .

In several preferred embodiments, formulations having a Young's modulus of at least 15 million psi and a specific modulus of at least 130 million psi that are readily formed into fibers having a relatively high fiber modulus, above 13 million inches, are described. These include glasses consisting essentially of about, in mols:

25% SiO_2 , 12% Li_2O , 12% MgO , 12% ZnO , 12% Al_2O_3 , 15% B_2O_3 and 12% Y_2O_3 ;

25% SiO_2 , 5% Li_2O , 20% MgO , 9% CaO, 2% CuO, 8% Al_2O_3 , 14% B_2O_3 , 14% Y_2O_3 and 3% TiO_2 ;

25% SiO_2 , 5% Li_2O , 20% MgO , 6% CaO, 2% CuO, 8% Al_2O_3 , 3% Fe_2O_3 , 14% Y_2O_3 and 3% TiO_2 ;

25% SiO_2 , 6% Li_2O , 20% MgO , 15% CaO, 4% ZnO, 2% CuO, 13% B_2O_3 , 12% Y_2O_3 and 3% TiO_2 ; and

25% SiO_2 , 15% Li_2O , 15% MgO , 15% CaO, 10% ZnO, 15% B_2O_3 , 5% Y_2O_3 .

In the middle three formulations, the glass has a Young's modulus above 17 million psi, a specific modulus above 140 million inches and yield fibers having a fiber modulus of approximately 16 million psi.

In several other preferred embodiments, formulations having a Young's modulus of at least 20 million psi and a specific modulus of at least 150 million inches are described. These include glasses consisting essentially of about, in mols:

24% SiO_2 , 12% Li_2O , 16% MgO , 12% CaO, 8% ZnO 3% Al_2O_3 , 10% B_2O_3 , 12% ZrO_2 and 3% TiO_2 ;

22% SiO_2 , 11% Li_2O , 22% MgO , 11% ZnO, 11% Al_2O_3 , 12% Y_2O_3 and 11% ZrO_2 ; and

25% SiO_2 , 15% Li_2O , 15% MgO , 15% CaO, 15% ZnO, 8% Al_2O_3 and 7% Y_2O_3 .

The first of the above three glasses exhibits a Young's modulus in excess of 22 million psi with a specific modulus of 200 million inches.

The features of the present invention will be discussed in greater detail in the description which follows and will become more evident therefrom to those skilled in the art.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

In general, it will be appreciated that the glasses of the present invention are a combination of silica, the single alkali oxide lithia, and a particular combination of alkaline earth, trivalent and tetravalent oxides. Like known invert glasses, such as those of Trap and Stevels, which however are comprised of several alkaline oxides and several kinds of alkaline earth oxides but do not include any trivalent oxides, the glasses of the present invention contain so little silica that a continuous silica network is not possible. It will be appreciated that such glasses may be characterized by a structural parameter Y which denotes the average number of bridging O ions. According to a rule of Zachariasen for silicate glass formation, which postulates that these silicate glasses should have a three-dimensional network in

which the SiO_4 tetrahedra share approximately three of their four oxygens with neighboring tetrahedra, commercial silicate glasses have Y values between 3.0 and 3.5. For ternary soda lime silica glasses it is not possible to lower appreciably the parameter Y below 3.0 and still obtain stable glasses. In contrast, the strongly "basic" or invert glasses of this invention generally have Y values of 2.0 or below and in some cases values of zero. In calculating the parameter Y , the following formula is used:

$$Y = 6 - 200/P$$

where $P = \text{mol } \% \text{SiO}_2$. It is readily seen that for an orthosilicate such as Na_2SiO_4 with 33 1/3 mol percent SiO_2 , Y has a value of 0 while a meta silicate with a 40 mol percent SiO_2 , Y has a value of 1.0 and leads to the formation of a tetrahedra. As will be seen hereinafter, all of the glasses of this invention have a total SiO_2 content of less than 50 mol percent, more precisely 40 mol percent or less, and in some cases as little as 15 percent. It thus becomes apparent that the prior concept that silicate glasses must have a three-dimensional network of SiO_4 tetrahedra cannot be maintained, even if the network modifiers are cations of the noble gas type. It is therefore considered that the present glasses lie between the tetrahedral structures of the conventional soda lime silicate glasses and the octahedral structures of some special glasses such as the Morey-Eastman Kodak optical glasses. In any event, the advantages of the present glasses will be recognized, not only because of their consistently high Young's modulus, specific modulus and in some cases, ready fiberizability, but also because they permit lowering of the liquidus temperature, greatly increase the field of glass formation and allow the study of the effect of the atomic structure of a glass upon its properties. As indicated above, invert glasses have been made according to the present invention with an elastic modulus in excess of 20 million pounds per square inch.

It has been determined that while low atomic number oxide components are a primary choice in achieving high modulus glass compositions of high specific modulus, they are not the only choice since contributions per mol percent to Young's modulus of several of the heavier elements were high, as follows:

Oxide	Contribution to Young's modulus per mol % (kilobars)
SiO_2	7.3
Al_2O_3	12.1
CaO	12.6
Li_2O	7.0
B_2O_3	7.2
ZnO	1.72
TiO_2	13.3
ZrO_2	18.9
MgO	12.0
Y_2O_3	24.3
La_2O_3	22.4
Ce_2O_3	18.6

and rising
with increas-
ing R_2O

and rising
with decreas-
ing R_2O and
 SiO_2 to 14.8

It has thus been found that the judicious use of the heavier oxides is obviously to be considered in cases where they improve viscosity, surface tension, working range and other characteristics.

It is to be noted that several rules which are predicated on experience with glasses comprised of silica networks do not hold true for the non-network invert glasses. It has, for example, been found that substitution of B_2O_3 for SiO_2 fails to decrease the density while the substitution of CuO for ZnO markedly lowers the density.

All of the compositions investigated were made by melting 500 gram batches of the specified raw materials in high purity (99.9 percent) alumina crucibles in air using kilns heated by Super-Kanthal hairpin electrical resistance elements. The starting materials used were 5 micron particle-size high purity silica, high purity alumina of 325 mesh, laboratory reagent grade magnesium oxide, 99.9 percent lanthanum oxalate, and other comparable materials such as reagent grade zinc carbonate or calcium carbonate. These materials yielded a water-white optical grade glass free of seed, stone and bubbles when properly compounded and held at temperatures of 1,000°-1,650°C for at least 2 hours. With the above technique, alumina crucibles of even slightly lower purity (99.3-99.7 percent) cannot be used. It is recognized however that the glasses may be prepared in beryllia crucibles in air and in the same kilns or in platinum crucibles in air in a platform kiln or in tungsten crucibles in purified argon or vacuum atmospheres.

The compositions of some of the representative glasses formulated in the course of the experimental program are set forth in Table I.

Table I

Ex- ample	Compositions of Representative Glasses (Mol Percent)													
	SiO_2	Li_2O	CaO	ZnO	MgO	CuO	Al_2O_3	Fe_2O_3	B_2O_3	La_2O_3	Y_2O_3	ZrO_2	TiO_2	Ce_2O_3
1	40	12	—	12	12	—	12	—	—	—	12	—	—	—
2	40	12	—	12	12	—	12	—	—	12	—	—	—	—
3	25	15	15	15	15	—	8	—	—	—	7	—	—	—
4	25	12	—	12	12	—	12	—	15	—	12	—	—	—
5	15	15	15	15	15	—	8	—	10	—	7	—	—	—
6	22	11	—	11	22	—	11	—	—	—	12	11	—	—
7	39	6	—	6	24	—	12	3	—	—	10	—	—	—
8	39	6	—	—	24	3	12	—	6	—	10	—	—	—
9	24	12	12	8	16	—	3	—	10	—	—	12	3	—
10	20	12	12	8	16	—	6	—	14	—	12	—	—	—
11	25	5	9	—	20	2	8	—	14	—	14	—	3	—
12	25	5	6	—	20	2	8	3	14	—	14	—	3	—
13	25	10	15	10	15	—	—	—	13	—	12	—	—	—
14	25	7	15	8	15	—	—	—	13	—	12	—	—	—
15	25	6	15	4	20	2	—	—	13	—	12	—	3	—
16	25	6	9	4	20	2	6	—	13	—	12	—	3	—

Table I - Continued

Ex- ample	Compositions of Representative Glasses (Mol Percent)														
	SiO ₂	Li ₂ O	CaO	ZnO	MgO	CuO	Al ₂ O ₃	Fe ₂ O ₃	B ₂ O ₃	La ₂ O ₃	Y ₂ O ₃	ZrO ₂	TiO ₂	CeO ₂	
17	38	6	9	4	20	2	6	—	—	—	12	—	3	—	
18	25	15	15	15	15	—	—	—	10	—	5	—	—	—	
19	39	6	—	6	24	—	12	—	—	—	10	—	—	3	
20	25	15	10	15	15	—	—	—	15	—	5	—	—	—	
21	24	12	12	8	16	—	3	3	10	—	—	12	—	—	
22	25	14	14	14	15	—	—	—	8	—	10	—	—	—	
23	25	13	13	13	13	—	—	—	13	—	10	—	—	—	
24	25	12	13	12	12	—	—	—	12	—	10	—	4	—	
25	25	13	13	13	12	—	—	—	12	—	10	—	2	—	
26	25	15	15	10	15	—	—	—	15	—	5	—	—	—	
27	25	14	14	8	14	—	—	—	15	—	10	—	—	—	
28	25	15	2	15	15	—	8	—	10.5	7	—	2	—	0.5	

Table I A

Ex- ample	(Weight Percent)														
	SiO ₂	Li ₂ O	CaO	ZnO	MgO	CuO	Al ₂ O ₃	Fe ₂ O ₃	B ₂ O ₃	La ₂ O ₃	Y ₂ O ₃	ZrO ₂	TiO ₂	CeO ₂	
1	29.5	4.4		12.0	5.9		15.0				33.2				
2	25.7	3.8		10.4	5.2		13.1			41.8					
3	21.4	6.4	12.0	17.4	8.6		11.6				22.6				
4	18.1	4.3		11.8	5.8		14.8	12.6	12.6		32.7				
5	12.7	6.3	11.8	17.2	8.5		11.5		9.8		22.2				
6	15.8	5.9		10.6	10.6		13.3				29.6	16.2			
7	29.6	2.3		6.2	12.2		15.4	6.0			28.5				
8	30.8	2.4			12.7	3.1	16.0		5.5		29.6				
9	22.2	5.5	10.4	10.0	9.9		4.7		10.7			22.8	3.7		
10	15.4	4.6	8.6	8.3	8.3		7.8		12.5		34.6				
11	18.0	1.8	6.1		9.7	1.9	9.8		11.7		37.9		2.9		
12	17.4	1.7	3.9		9.3	1.3	9.5	5.6	11.3		36.7		2.8		
13	19.6	3.9	11.0	10.6	8.0				11.8		35.4				
14	19.4	2.7	10.9	8.4	7.8	2.1			11.7		35.0		2.1		
15	19.5	2.7	10.9	4.2	10.5	2.1			11.8		35.2		3.1		
16	18.9	2.6	6.3	4.1	10.1	2.0	7.7		11.4		34.0		3.1		
17	29.7	2.4	6.3	4.1	10.2	2.5	7.6				33.8		3.8		
18	23.4	7.0	13.1	19.0	9.4				10.8		17.8				
19	27.8	2.1		5.8	11.6		14.5				26.8			11.7	
20	23.1	6.9	8.6	18.7	9.3				16.0		17.3				
21	21.4	5.3	10.0	9.7	9.6		4.6	7.1	10.4			22.0			
22	20.7	5.8	10.8	15.7	8.3				7.7		31.1				
23	20.4	5.3	9.9	14.3	7.1				12.3		30.6				
24	20.2	4.7	9.8	13.1	6.5				11.2		30.3		4.3		
25	20.3	5.2	9.8	14.3	6.5				11.3		30.5		2.2		
26	23.5	7.0	13.1	13.1	9.4				16.3		17.6				
27	19.5	5.4	10.2	14.8	7.3				13.5		29.3				
28	18.5	5.5	1.4	15.0	7.4		10.0		9.0	28.1		3.2		2.0	

In order to characterize the various glasses, measurements of the density and Young's modulus of bulk samples as well as Young's modulus of mechanically drawn fibers were made. As a standard density measuring technique, the heavy-liquid-of-known density comparison procedure was used for samples with densities less than 3.00 gms/cm³ while the Archimedeian method was employed for samples with densities greater than 3.00 gms/cm³.

Bulk sample for modulus measurement were prepared using the technique whereby the samples were drawn directly from the crucibles of molten glass into fused silica tubes previously dusted lightly with powdered magnesia. Controlled suction for pulling the sample into the tube was supplied by a hypodermic syringe. Since all of the experimental glasses had coefficients of thermal expansion at least higher than that of fused silica, the aspirated bars shrank away from the tube upon cooling and thus were readily removable.

Table II lists the values for a number of glasses made and tested in accordance with the teachings herein.

As is evident from the Tables, several of the formulations have proved to display extremely high modulus as well as modulus/density ratios superior to the best of glass compositions heretofore known. The particular

Table II

Example	Glass Density, Young's Modulus and Specific Modulus		
	Density lb./in. ³	Young's Modulus psi × 10 ⁶	Specific Modulus 10 ⁶ in.
1	0.1296	17.9	138
2	0.1347	18.4	137
3	0.1275	20.3	159
4	0.1200	15.7	131
5	0.1217	17.6	144
6	0.1095	20.7	189
7	0.1260	18.6	148
8	0.1289	19.3	149
9	0.1136	22.8	200
10	0.1210	16.8	139
11	0.1198	17.8	148
12	0.1220	17.2	140
13	0.1188	18.2	154
14	0.1268	16.9	133
15	0.1223	18.1	148
16	0.1212	17.8	146
17	0.1303	18.9	145
18	0.1186	16.0	135
19	0.1365	18.1	132
20	0.1144	15.9	139
21	0.1082	17.7	163
22	0.1242	17.3	140
23	0.1215	16.8	138
24	0.1198	16.5	137
25	0.1235	17.5	142
26	0.1105	16.1	146
27	0.1193	16.7	140
28	0.1313	15.5	118

formulation selected in a given application, however, will be dependent usually not only upon the properties of the end product but also upon the cost of the ingredients included. This is particularly true in commercial production.

Several of the glasses proved to be fiberizable. In order to evaluate these glasses, a "poor man's bushing" was used to prepare mechanically drawn fibers. The bushing comprises a 20 cm³ platinum crucible with a reinforced bottom and central orifice. The orifice is formed by welding several thicknesses of platinum foil to the bottom of a normal platinum crucible until a bottom thickness of three-sixteenths in. is obtained. A central orifice 0.088 in. at top, 0.063 in. at bottom and three-sixteenths in. long in the crucible is made by taper reaming. Once the orifice is made, the crucible is filled with glass and introduced into a platform furnace having high temperature Super-Kanthal hairpin heating elements together with a first ring orifice to provide water cooling immediately below the crucible and a second ring orifice to cool the fiber with helium jets as it forms. The fibers were drawn at speeds of 4,000-8,000 feet/minute and yielded circular glass fibers having a diameter of approximately 1 mil. The fibers were then evaluated on an Instron CRE tester operated with a machine speed of 0.2 in./minute, a chart speed of 20 in./minute, a gage length of 5 in. and a full scale capacity of 1.0 lb. The specimens were held in air actuated clamps with flat rubber coated faces. Table III lists the values for several glasses which were mechanically drawn into fibers.

Table III

Example	Fiber Modulus	
	Young's Modulus psi x 10 ⁶	
4	13.6	
11	16.5	
12	16.1	
15	15.8	
26	14.8	

In general for the purposes of this invention, the lower molecular weight divalent oxides are preferable to the higher molecular weight divalent oxides. For example, MgO and CaO are to be preferred in comparison to SrO and BaO and AnO and CuO in comparison to CdO and HgO. Further, the lower weight trivalent oxides Al₂O₃, B₂O₃ and Fe₂O₃ are preferred in comparison to Ga₂O₃ and In₂O₃ and likewise Sc₂O₃, Y₂O₃ and La₂O₃ (lower molecular weight trivalent oxides of Group IIIB) are preferred in comparison to Nd₂O₃, Sm₂O₃, Gd₂O₃ and Er₂O₃. Similarly, the lower molecular weight tetravalent oxide SiO₂ is preferred to GeO₂, SnO₂ and PbO₂ and the lower molecular weight tetravalent oxides TiO₂ and ZrO₂ of Group IVB are to be preferred as compared to HfO₂ and ThO₂. Finally, the lowest molecular weight monovalent oxide Li₂O is preferred in comparison to Na₂O, K₂O, Rb₂O and Cs₂O. The above preferences are based on the requirements that the densities of the resulting glasses must be as low as possible, the cohesive bond energy as great as possible,

and the field strength of the ions as high as possible.

Of course, the glass compositions may contain certain additional tetravalent or sesquivalent oxides or fluorides commonly employed in optical glassmaking such as tantalum pentoxide (Ta₂O₅) or tungsten trioxide (WO₃) in slight amounts.

While the invention has been described in connection with a number of particular preferred embodiments, they are considered illustrative only and no limitation is intended thereby. Various alterations and modifications will be evident to those skilled in the art within the true spirit and scope of the invention as set forth in the appended claims.

What is claimed is:

1. A fiberizable glass composition having a Young's modulus of at least 15 million psi and a specific modulus of at least 130 million inches consisting essentially of about, in mols:

25% SiO₂; 12% Li₂O; 12% MgO; 12% ZnO; 12% Al₂O₃; 15% B₂O₃ and 12% Y₂O₃.

2. A fiberizable glass composition having a Young's modulus of at least 17 million psi and a specific modulus of at least 140 million inches consisting essentially of about, in mols:

25% SiO₂; 5% Li₂O; 20% MgO; 9% CaO; 2% CuO; 8% Al₂O₃; 14% B₂O₃; 14% Y₂O₃ and 3% TiO₂.

3. The glass composition of claim 2 wherein said CaO content is 6 percent and Fe₂O₃ is present in an amount of 3 percent.

4. A fiberizable glass composition having a Young's modulus of at least 17 million psi and a specific modulus of at least 140 million inches consisting essentially of about, in mols:

25% SiO₂; 6% Li₂O; 20% MgO; 15% CaO, 4% ZnO; 2% CuO; 13% B₂O₃; 12% Y₂O₃ and 3% TiO₂.

5. A fiberizable glass composition having a Young's modulus of at least 16 million psi and a specific modulus of at least 140 million inches consisting essentially of about, in mols:

25% SiO₂; 15% Li₂O; 15% MgO; 15% CaO; 10% ZnO; 15% B₂O₃; 5% Y₂O₃.

6. A glass composition having a Young's modulus of at least 20 million psi and a specific modulus of approximately 200 million inches consisting essentially of about, in mols:

24% SiO₂; 12% Li₂O; 16% MgO; 12% CaO; 8% ZnO; 3% Al₂O₃; 10% B₂O₃; 12% ZrO₂ and 3% TiO₂.

7. A glass composition having a Young's modulus of at least 20 million psi and a specific modulus of approximately 189 million inches consisting essentially of about, in mols:

22% SiO₂; 11% Li₂O; 22% MgO; 11% ZnO; 11% Al₂O₃; 12% Y₂O₃ and 11% ZrO₂.

8. A glass composition having a Young's modulus of at least 20 million psi and a specific modulus of approximately 159 million inches consisting essentially of about, in mols:

25% SiO₂; 15% Li₂O; 15% MgO; 15% CaO, 15% ZnO; 8% Al₂O₃ and 7% Y₂O₃.

* * * * *